



# B28N230

## Product Technical Information

B28N230 is an unstabilised copolymer of ethylene and butyl acrylate containing 15 % butyl acrylate. It is designed for compounding within wire & cable applications. It can accept high amounts of fillers and could be used as base polymer for a Flame Retardant Compound.

Properties	Test Method	Value	Units <sup>(1)</sup>
<b>Physical</b>			
Melt flow rate	ISO 1133 Cond. D	8.0	g/10min
Conventional density Conditioning ISO 1872/1	ISO 1183 Method D	924	kg/m <sup>3</sup>

(1) Data should not be used for specification work

## Packaging

B28N230 is sold in pellet form and is available in the following packaging: 1.0 ton (nominal) octabins.

## Storage and handling

B28N230 should be stored in dry conditions and temperature below 60°C and protected from UV-light. Improper storage can initiate degradation with resulting odor generation and color changes.

## Safety

B28N230 is not classified as a dangerous preparation.

Dust and fines from the product may give a risk for dust explosion. All equipment should be properly earthed.

Inhalation of dust may irritate the respiratory system and should be avoided.

During processing of the product small amounts of fumes are generated, which require proper ventilation.

February, 2008

Published by  
**INEOS Polyolefins**



# B28N230

## Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, send an email to [psnohreg@innovene.com](mailto:psnohreg@innovene.com). Unless specifically indicated, the products mentioned herein are not suitable for applications in the medical or pharmaceutical sector.

## Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Material Safety Data Sheet (MSDS) that may be obtained from the website [www.ineospolyolefins.com](http://www.ineospolyolefins.com). Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

## Exclusion of Liability

Although INEOS POLYOLEFINS endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS POLYOLEFINS is accurate and up to date, no representation or warranty, express or implied is made by INEOS POLYOLEFINS as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS POLYOLEFINS is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS POLYOLEFINS are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS POLYOLEFINS is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS POLYOLEFINS materials are suitable for the particular purpose intended and INEOS POLYOLEFINS shall not be responsible for any loss or damage caused by misuse of INEOS POLYOLEFINS products. To the maximum extent permitted by law, INEOS POLYOLEFINS accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS POLYOLEFINS materials or the use of INEOS POLYOLEFINS materials in conjunction with such other materials.

February, 2008

Published by  
**INEOS Polyolefins**