



BPD2000E

Product Technical Information

BPD2000E is an unstabilised low density thermoplastic polyethylene. It is designed for use in medium voltage power cable insulation and applications requesting extra cleanliness using the direct peroxide injection (DPI) process.

Specification

BPD2000 meets the following material specification:

- ISO 1872/1-PE, KHN, 23-D022
- ASTM D-1248 AI 3, Grade E5

Regulations and approvals

Crosslinked cables produced with BPD2000 insulation meet the following industry cable specifications:

- IEC 502
- AEIC : CS5
- EdF: HN 33-S-23

Packaging

BPD2000 is sold in pellet form and is available in the following packaging : 1.1 ton octabins and bulk tankers.

Processing Data

BPD2000 will be extruded in conjunction with standard peroxide injection practice. An antioxidant has to be introduced by the user in order to fulfill the required ageing tests. The required extrusion melt temperature is approximately 135°C or 145°C depending on peroxide nature.

Properties	Test Method	Value ⁽¹⁾	Units
Physical			
Melt flow rate	ISO 1133 Cond. D	2.0	g/10min
Conventional density conditioning ISO 1872/1	ISO 1183 Method D	923	kg/m ³
Tensile strength @ break	IEC 811-1-1	18	MPa
Elongation @ break	IEC 811-1-1	> 500	%

February, 2008

Published by
INEOS Polyolefins



BPD2000E

Electrical

Dielectric constant @ 50 Hz	ASTM D 150	2.30	-
Dissipation factor @ 50 Hz	ASTM D 150	300	μrad
DC volume resistivity @ 23°C	ASTM D 257	> 10 ¹⁵	Ω cm
Dielectric strength, short time	ASTM D 149	> 22	kV/mm

(1) Tests on moulded crosslinked plaques prepared according to INEOS Polyolefins method. Data should not be used for specification work.

Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, send an email to psnohreg@innovene.com. Unless specifically indicated, the products mentioned herein are not suitable for applications in the medical or pharmaceutical sector.

Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Material Safety Data Sheet (MSDS) that may be obtained from the website www.ineospolyolefins.com. Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

Exclusion of Liability

Although INEOS POLYOLEFINS endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS POLYOLEFINS is accurate and up to date, no representation or warranty, express or implied is made by INEOS POLYOLEFINS as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS POLYOLEFINS is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS POLYOLEFINS are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS POLYOLEFINS is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS POLYOLEFINS materials are suitable for the particular purpose intended and INEOS POLYOLEFINS shall not be responsible for any loss or damage caused by misuse of INEOS POLYOLEFINS products. To the maximum extent permitted by law, INEOS POLYOLEFINS accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS POLYOLEFINS materials or the use of INEOS POLYOLEFINS materials in conjunction with such other materials.

February, 2008

Published by
INEOS Polyolefins